



Topplack PU 4020

Product Description:

Hagmans Topplack PU 4020 is a moisture-curing, single-component urethane varnish, with extremely good light-resistance and gloss-retention.

Range of Applications:

Over-coating of flake and coloured-sand coatings, outdoor floor paints and where there is a high requirement for light-resistance.

Technical Data:

Curing time at +15°C: Approx. 8 hours before the next coat can be applied. The painted floor may be walked on after approx. 24 hours, and achieves full wear-strength after 5-7 days.
NOTE! Lowest floor temperature +5°C.

Gloss value: Approx. 90, high gloss
Fire risk: Fire risk
Material consumption: Approx. 0.120 lit./coat on smooth surface.
1 lit. covers approx. 8 m².
Shelf life: 2 years.
Dry content: 50%
Specific gravity: 1,0
Colour: Clear

Application:

Hagmans Topplack PU 4020 can be applied by brush or roller. The substrate must be clean and dry. Should be applied in two coats. At approx. 60% atmospheric humidity, the next coat can be applied after 8 hours. If the subsequent coat cannot be applied before 18 hours, the varnish must be sanded matt. May be thinned with Förtunning 450/2, which is also suitable for cleaning tools.

Packs:

Article number:
38531 1 lit.
38533 5 lit. 38535 10 lit.



0417