

Kallasfalt (Cold Asphalt)

Product description:

An asphalt solution intended to insulate against moisture.

Areas of use:

Moisture insulation of masonry and cement surfaces above and below ground level.

Technical information:

Basic material:	Asphalt solution
Density:	0.93 kg/l
Material consumption:	2-4 m ² /l depending on substrate
Drying time:	approx. 6 h at 20°C
Lowest application temp:	+5 °C
Colour:	Black
Pot life:	2 years.

Preparation:

The foundation must be dry and clean.

Instructions for use/Application:

Apply with a brush, paintbrush or roller. Untreated cement surfaces must be primed with **Hagmans Asfaltprimer** (asphalt primer) alt. **Hagmans Kallasfalt** (cold asphalt) diluted with 20 % mineral spirits (solvent naphtha). Then apply 1 layer of undiluted **Kallasfalt** (cold asphalt).